

Test Report

Applicant : XI'AN METALS & MINERALS I/E CO.,LTD.
6F.,JIA XIANG INT'L TRADE BLDG.,216 SOUTH HAN GUANG
RD.,XI'AN,CHINA
Attn : WANG XIN

NUMBER : TSNH00242149

Date : Aug 28, 2017

Sample Description:

One (1) submitted sample said to be
Item Name :GRANITE ROLLING PIN
Item No. :63771
Style No. :63771
Buyer :BLOMUS GBMH
Material :GRANITE
Supplier/Manufacturer :XIAN METALS & MINERALS I/E CO.,LTD
Country of Destination :DE
Country of Origin :CN

Tests Conducted:

As requested by the applicant, for details refer to attached page(s).

Conclusion:

According to the test results of below test parameters, and based on the provided material information, submitted sample complied with the suggested food contacting testing parameters for German §30 and §31 LFGB and also complied with general requirement of regulation (EU) 10/2011 and (EC) 1935/2004 article 3,paragraph 1

Tests conducted:

Based on the assessment of the submitted sample and the information provided, the following tests had been conducted :

- 1) Sensory test on finished product
 - 2) Leachable Pb, Cd & Co (Internal) content on ceramic
- *****

To be continued

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.



David Zhang
Senior Manager



Test Report

NUMBER : TSNH00242149

1. Leachable Lead And Cadmium And Cobalt Content

As per §64 LFGB B80.03-1 and B80.03-2, by Atomic Absorption Spectrophotometric (AAS) or Inductively Coupled Argon Plasma (ICP) analysis.

<u>Tested Component</u>	<u>Surface Area (dm²)</u>	<u>Volume of leaching Solution (mL)</u>	<u>Lead (mg/dm²)</u>	<u>Result Cadmium (mg/dm²)</u>	<u>Cobalt (mg/L)</u>
(1)	4.7	1700	<0.05	<0.03	<0.03
(2)	1.8	470	<0.05	<0.03	<0.03
		Limit (flatware):	0.8	0.07	0.05

Tested Components:

- (1) granite rolling pin for sample use
- (2) granite shelf for sample use

To be continued

Test Report

NUMBER : TSNH00242149

2. Sensory Evaluation

With reference to §64 LFGB I00.90-6.

Test procedure:

Sample was thoroughly rinsed with distilled water and then totally immersed by distilled water. Filled sample was kept at ambient temperature 20°C and relative humidity (40-80%) for 20h. Off-odor and off-taste was evaluated with 5 panelists using control sample of distilled water.

	<u>Result</u>		<u>Limit</u>
	(1)	(2)	
Appearance	Clear, Colourless	Clear, Colourless	Clear, Colourless
Odor	0	0	2.5
Taste	0	0	2.5

Assessment:

Intensity scale:

0 = No perceptible odour / taste

1 = Odour / taste just perceptible (but still difficult to define)

2 = Slight odour / taste

3 = Distinct odour / taste

4 = Strong odour / taste

Tested Components:

(1) granite rolling pin for sample use

(2) granite shelf for sample use

Date sample received: Aug 22, 2017

Testing period: Aug 22, 2017 to Aug 25, 2017

To be continued

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

Test Report

NUMBER : TSNH00242149

Photo:



End of report